

ZANELLI COMMERCIALE S.r.L.

**REPAIR PATCH "ZR60" and REPAIR SEALANT "ZS60"
 TECHNICAL DATA SHEET
 (document nr. QA – 04.03 dated 10/2001 page 1 of 1 - tentative)**

SYSTEM PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUE	SERVICE TEMPERATURE
REPAIR PATCH			
Peel to P.E.	ASTM D-1000	4,50 kg/cm	60°C
Cathodic disbondment	ASTM G-42 x 30 dd.	13 mm. max,	60°C
Impact resistance	DIN 30672 cl. C	≥ 15 Nm	60°C
REPAIR MASTIC			
Softening Point	ASTM E-28	94°C ± 5°C	60°C
Shear Strength	ASTM D-1002	350 PSI at 23°C	60°C

PRODUCT SIZE

TYPE	CODE	SHAPE	THICKN.	WIDTH	LENGTH
REPAIR PATCH	ZR60	ROLL	0,8 mm.	0,450 mm.	10.000 mm.
REPAIR MASTIC	ZS60	ROLL	3,5 mm.	50 mm.	3.000 mm.